



Report prepared for:
Arro-Mark Company L.L.C.
George Pappageorge
Partner
158 West Forest Avenue
Englewood, NJ 07631
Phone: 201-567-4112
Fax: 201-567-1373
Email: arromark@aol.com

Report prepared by:
Salvador Pastor

For further assistance, contact:
Salvador Pastor
Technical Manager
PO Box 51610
Knoxville, TN 37950-1610
Phone: 865-546-1335
Email: salpastor@galbraith.com

RESULTS OF ANALYSIS
SAMPLE NUMBER
Black XV-12149 Felt Tip Ink, Batch # XV-12586
Lab ID: 2014-W-9001

Analysis	Results (ppm)	Requirements (ppm)
Total Halogens:	250 maximum
Bromine	<21 ppm	100 maximum
Chlorine	46 ppm	100 maximum
Fluorine	<22 ppm	100 maximum
Iodine	<7 ppm	100 maximum
Lead	<4.53 ppm	25 maximum
Sulfur	<7 ppm	250 maximum
Low Melting Point Elements:	300 maximum
Sodium	13 ppm	100 maximum
Boron	<4.53 ppm	100 maximum
Phosphorus	<4.53 ppm	100 maximum
Cadmium	<4.53 ppm	100 maximum
Antimony	<4.53 ppm	100 maximum
Bismuth	<4.53 ppm	100 maximum
Mercury	<0.0272 ppm	100 maximum
Zinc	<4.53 ppm	100 maximum
Tin	<4.53 ppm	100 maximum
Tellurium	<4.53 ppm	100 maximum
Selenium	<4.53 ppm	100 maximum
Silver	<4.53 ppm	100 maximum
Thallium	<4.53 ppm	100 maximum
Copper	<4.53 ppm	100 maximum

Meets GE Specification # D50TF8-S7

Signatures:

Published by: Salvador Pastor

• Physical signatures are on file.

• -Published By- signature indicates authorized release of data.

• Analytical Method on file.